

Data sheet P 580

Revision 2

1. CHEMICAL COMPOSITION

"P580" is a special nonmagnetic, austenitic Mn-Cr-N-steel with a high pitting corrosion resistance, specifically developed for oilfield applications.

С	Mn	Cr	Ni	Мо	N
max. 0,06	22,00-24,50	20,50-22,00	max. 2,50	max. 1,50	min. 0,75

2. MECHANICAL PROPERTIES

Following mechanical properties (tested at room temperature) are achieved by a special cold-working process over the full length of the collar:

Yield Strength (min.): OD up to 91/4"	140 ksi	965 N/mm ²
0,2%-offset method OD 91/2" and larger	130 ksi	900 N/mm ²
Tensile Strength (min.):	150 ksi	1035 N/mm ²
Elongation (min.):	20%	20%
Reduction of area (min.):	50%	50%
Impact energy (min.):	60 ft.lb	82 J
Endurance Strength / N=10 ⁷ (min.):	60 ksi	414 N/mm ²
Hardness Brinell:	350-450 HB	350-450 HB

3. MAGNETIC PROPERTIES

Relative permeability: $\leq 1,001$.

4. CORROSION RESISTANCE

- Transgranular SCC: Prevented by special surface treatments (Hammer peening, roller burnishing, shot peening).
- Intergranular SCC: The occurrence of material sensitization is prevented by quenching after warmforging. Each collar is tested according to ASTM A 262, Pract.A and E, last edition.
- **Pitting Corrosion:** Due to the very high chromium- and nitrogen contents an excellent resistance to pitting corrosion is given. A PRE-value (PRE=Cr+3,3.Mo+16.N) of min. 37 is guaranteed.

5. NON-DESTRUCTIVE TESTING

- Magnetic inspection: Drill collars are 100% tested by a proprietary probe-testing process using a Förster Magnetomat 1.782. ("Hot Spot"-test). Magnetic permeability of each collar is certified with the printout of probe-testing.
- **Ultrasonic inspection:** Each collar is ultrasonically inspected over 100% of the volume according to ASTM E 114, last edition as a minimum level.

P580 Non-Magnetic Drill Collars meet all requirements of API Spec. 7.1, last edition All tests are carried out according to ASTM-Standards, last editions.

Prepared / released: B. Holper

Date: June, 2013